

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 11-149180

(43)Date of publication of application : 02.06.1999

(51)Int.Cl.

G03G 9/087

(21)Application number : 09-333611

(71)Applicant : SANYO CHEM IND LTD

(22)Date of filing : 17.11.1997

(72)Inventor : FUKUSHIMA HAJIME  
NAKANISHI HIDEO

## (54) DRY TONER AND ITS PRODUCTION

## (57)Abstract:

PROBLEM TO BE SOLVED: To obtain a dry toner excellent in powder flowability, low temp. fixability and anti-hot offsetting property and not requiring a producing process such as comminuting by incorporating particles formed by the extension reaction and/or crosslinking reaction of an isocyanato group-contg. prepolymer with amines in an aq. medium.

SOLUTION: The dry toner contains a binder component comprising resin particles formed by the extension reaction and/or crosslinking reaction of an isocyanato group-contg. prepolymer with amines in an aq. medium. The wt. average mol.wt. of the prepolymer is  $\geq 10,000$ , preferably 20,000-10,000,000, especially preferably 30,000-1,000,000 from the viewpoint of anti-hot offsetting property. The isocyanato group-contg. prepolymer is, e.g. an isocyanato group-contg. polyester prepolymer or an isocyanato group-contg. epoxy resin prepolymer. The amines are, e.g. compds. obtd. by blocking polyamines with a releasable compd.

## LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]